

Block Compression Test Results**		
Name	Weight (pounds)	Resistance (KN)
Hullkrete secret recp	22.19	60
Hullkrete 1	11.67	8
Paperkrete 1 A***	17.99	28
Paperkrete 1 B	15.64	20
Hullkrete second Vasquez	17.01	24
Paperkrete 1 C	16.79	18
Hullkrete superconcrete A	22.1	60
Hullkrete superconcrete B	22.8	62
Hullkrete Vasquez Final A	20.7	30
Hullkrete Vasquez Final B	21.46	28
Hullkrete Vasquez Final C	22.28	30
Paperkrete 2 A*	17.15	9
Concrete Normal Ash****	31.97	100

Note: The compression machine did not cover the entire block during these tests, thus the measured strengths are likely to underrepresent the true strength of the blocks.

*This papercrete block was not completely dry at the time of testing, which accounts for discrepancies in strength.

**These tests were conducted at UNIBE with a machine brand "Hi-Tech Education" model HPM 3/2.

***Letters at the end of a block name specify another block of the same mixture.

****Comparison block - includes no rice hull nor paper

true strength of the blocks. As it was the machine compressed the center of the block lengthwise.

